



Blue Tea Mediated Synthesis and Characterisation of Copper Nanoparticles: An *In-vitro* Study

Rinki Susan George^a, Arvina Rajasekar^{bt*} and S. Rajeshkumar^{c#}

^a Saveetha Dental College and Hospitals, Saveetha Institute of Medical and Technical Sciences, Saveetha University, Chennai-77, Tamil Nadu, India.

^b Department of Periodontics, Saveetha Dental College and Hospitals, Saveetha Institute of Medical and Technical Sciences, Saveetha University, Chennai-77, Tamil Nadu, India.

^c Department of Pharmacology, Saveetha Dental College and Hospitals, Saveetha Institute of Medical and Technical Sciences, Saveetha University, Chennai-77, Tamil Nadu, India.

Authors' contributions

This work was carried out in collaboration among all authors. All authors read and approved the final manuscript.

Article Information

DOI: 10.9734/JPRI/2021/v33i63B35646

Open Peer Review History:

This journal follows the Advanced Open Peer Review policy. Identity of the Reviewers, Editor(s) and additional Reviewers, peer review comments, different versions of the manuscript, comments of the editors, etc are available here: <https://www.sdiarticle5.com/review-history/77923>

Original Research Article

Received 20 October 2021
Accepted 27 December 2021
Published 29 December 2021

ABSTRACT

Background: Nanoparticles (NPs) are often regarded as essential components of nanotechnology. Butterfly-pea flower tea, often known as Blue Tea, is a caffeine-free or herbal tea produced from an infusion of the *Clitoria ternatea* plant's flower petals. In the creation of nanoparticles, plant extracts may act as reducing and stabilizing agents.

Aim: The study's goal was to evaluate the characterization of copper nanoparticles derived from blue tea.

Materials and Methods: The green synthesis approach was used to make the blue tea mediated copper nanoparticles. UV spectrometry and transmission electron microscopy were used to examine morphological characteristics such as form and size of the green produced copper nanoparticles.

Results: The results revealed that the nanoparticles mediated by blue tea extract were eco-friendly, excellent, and non-toxic. Copper nanoparticles were well disseminated and crystalline in nature, according to TEM pictures. Copper nanoparticles were spherical in shape. The particles

[†]Senior Lecturer;

[#]Associate Professor;

^{*}Corresponding author: E-mail: arvinar.sdc@saveetha.com;

were 5-10 μl in size. The TEM image showed that nanoparticles were not mixed, but were separated by equal interspaces between them, as validated by microscope visualization at a greater resolution.

Conclusion: Using blue tea, a simple, biological, and low-cost method for the manufacture of copper nanoparticles was developed in this study. To determine the efficacy of these nanoparticles, the generated copper nanoparticles can be exposed to several biological activities such as antibacterial, antifungal, and cytotoxic evaluation.

Keywords: Butterfly pea; *Citoria ternatea*; green synthesis; innovative; nanoparticles.

1. INTRODUCTION

Nanoparticles (NPs) are thought to be the basic building blocks of nanotechnology [1] due to their exceptional electron catalytic activity, metal nanoparticles are widely used in a variety of electrochemical, electro analytical and bio-electrochemical applications [2]. CuNPs (copper nanoparticles) are fascinating because of their unique features, which include a high surface-to-volume ratio, high yield strength, ductility, hardness, flexibility, and stiffness.

In a variety of applications, CuNPs showed excellent catalytic, antibacterial, antioxidant, and antifungal activity, as well as cytotoxicity and anticancer effects [3]. The creation of copper nanoparticles using blue tea was done in this study in a simple, biological, and low-cost manner [4]. To determine the efficacy of these nanoparticles, the synthesized copper nanoparticles can be exposed to several biological activities such as antibacterial, antifungal, and cytotoxic evaluation. Therefore they can be used in daily purposes as a substitute for conventional products and help in the betterment of life [5].

Plant extracts are very useful as they may act as reducing and stabilizing agents for the synthesis of nanoparticles [6]. The plant extract mentioned in the study, *Clitoria ternatea*, is commonly known as butterfly pea, which is a perennial herbaceous plant from the Fabaceae family. Butterfly-pea flower tea commonly known as Blue Tea is a caffeine free or herbal tea, beverage made from infusion of the flower petals of the *Clitoria ternatea* plant. These plants have been widely used in traditional medicine, particularly as a supplement to enhance cognitive functions and alleviate symptoms of numerous ailments including fever, inflammation, pain, and diabetes. The novel anthocyanins from *C. ternatea* were termed as "ternatins" which render *C. ternatea* flowers with their vivid blue color were isolated. In addition to it there were

abundant unique anthocyanins alongside other secondary metabolites in *C. ternatea* which makes the plant an ideal source of natural additives that can enhance the appearance and nutritive values of consumer products for various pharmacological activities.

There are several methods for synthesis of nanoparticles which includes metal vapour deposition, electrochemical reduction, thermal decomposition, chemical reduction etc from which chemical reduction is the highly preferred method among all other methods as it is simple and economical. The chemical reduction methods use separate reducing and stabilizing agents which are known to generate copper nanoparticles with controlled size and shape. The morphology and size of the copper nanoparticles were investigated and evaluated using the Scanning Electron Microscope and Transmission Electron Microscope. The transmission electron microscope was employed to characterize the size, shape and morphology of the prepared copper nanoparticles. The SEM is used mainly to generate high-resolution images of shapes of objects, to reveal the spatial variations in the chemical compositions external morphology (texture), chemical composition, and crystalline structure of the generated nanoparticles. The biosynthetic pathway for the preparation of nanoparticles potentially eliminates the toxicity and makes the nanoparticles more biocompatible [7]. Among the various biosynthetic approaches, the plant extracts has many advantages which includes easily available, safe to handle, possess a broad viability of metabolites, eliminating the cumbersome process such as maintaining the cell culture and extraction and separation can be easily scaled up for the large-scale synthesis of nanoparticles using biosynthesis [8]. The main phytochemicals which are responsible for the synthesis of nanoparticles are terpenoids, flavones, ketenes, aldehydes amines etc [9]. The green synthesis of copper nanoparticles is an eco-friendly procedure which uses natural

solvent that requires no toxic solvents and no dangerous material for the environment [10-19].

Our team has extensive knowledge and research experience that has translated into high quality publications [20–39] The aim of the study was to synthesize and characterize blue tea mediated copper nanoparticles using UV spectrometry transmission electron microscope (TEM).

2. MATERIALS AND METHODS

2.1 Preparation of Blue tea Extract

A sample of blue tea powder was taken and measured accurately to 1g to which 100mL of distilled water was added and boiled for 15-20 minutes at 60-70 degrees and the obtained extract was cooled for some time, then the solution was filtered by using whatman no.10 filter paper. The filtered extract was collected and stored in the refrigerator for further use.



Fig. 1. Mixture of blue tea extract in distilled water



Fig. 2. Concentrated extract of Blue tea extract

2.2 Synthesis of Copper Nanoparticles

Synthesis of copper nanoparticles was done biologically using blue tea. 20mM of copper sulphate was added to the obtained extract. The colour change was observed visually and photographed. The solution was kept in a magnetic stirrer for nanoparticle synthesis. The reaction mixture of copper sulphate and blue tea was centrifuged at 8,000xg for 10 minutes. The resulting pellet was washed three times with distilled water and filtered and the supernatant so formed was collected.




Fig. 3. Mixture of copper sulphate and Blue tea



Fig. 4. Blue tea mediated CuSO_4

2.3 UV Spectrometric Analysis of Synthesized Nanoparticle

Spectrometric analysis was evaluated by UV-visible spectroscopy. The biologically reduced

solution mixture was scanned by Shimadzu, Lambda UV mini-1240 instrument operated at a resolution of 1 nm. The UV-visible analysis was performed in the absorption wavelength of 200 to 700 nm periodically for one hour to observe rapid reduction of copper nanoparticles and the results were recorded for the graphical analysis.

2.4 Characterization of Prepared Copper Nanoparticles

The synthesized Cu NPs were characterized using TEM (Transmission Electron Microscope). The morphological analysis of the particles was done with TEM. A sample of Cu NPs was loaded on a carbon-coated copper grid, followed by solvent evaporation at room temperature for an hour. The TEM micrograph images were recorded on Zeiss- EM10C instrument on carbon coated copper grids with an accelerating voltage of 80 KV. The clear microscopic views were observed and documented in different ranges of magnifications.

3. RESULTS

The synthesized copper nanoparticles were predicted through the visual observation of solution colour change from light purple to dark purplish blue colour. The colour change signifies the presence of copper nanoparticles which was thereby confirmed by the UV-Visible spectrophotometer.

Copper nanoparticles were successfully synthesized using blue tea extract after being

subjected to continuous heat and stirring. The purple reaction mixture slowly changed to a thick purplish blue suspension after several minutes of the reaction. The development of intense purplish blue in colour owing to the surface plasmon resonance confirmed the synthesis of the copper nanoparticles. Colour changes of the reaction mixture 240 minutes after the bioreduction process, which were recorded by UV-visible spectrophotometer. UV-Visible readings were recorded in the wavelength range of 200 - 600nm. The absorption formed in the reaction media has an absorbance peak at 570nm. The surface plasmon resonance absorbance was very sensitive to size and shape of the particles. It was observed that the SPR bands were located at the range 570 nm which is the characteristic absorption peak for copper nanoparticles in this study [Fig. 5].

The centrifuged substrate was then subjected for the TEM analysis for the characterization so as to determine the size, shape and distribution of nanoparticles. TEM images showed that particles were well dispersed, crystalline in nature as shown in the Fig. 5. Copper nanoparticles were spherical in nature. The particle size was ranging from 5 to 10 microns in size. The TEM image showed that nanoparticles were not combined but were separated by equal interspaces between the particles, which were confirmed by microscopy visualizing under the higher resolution. This image explains that the copper nanoparticles are bounded with the phytochemicals of the plant extract [Fig. 6].




Fig. 5. UV-Visible Spectrophotometer's image depicting the synthesis of copper nanoparticles using blue tea extract. The X axis represents the wavelength (nm) and the Y axis represents absorbance (Abs). The UV visible spectra of the copper nanoparticles showed a peak of 570 nm.




Fig. 6. TEM image which confirmed the synthesis of CuNPs, which were crystalline, spherical in shape with an average size 5-10 microns

4. DISCUSSION

The current study was undertaken to synthesize and characterize blue tea mediated copper nanoparticles which could be used as adjuncts in medical and dental fields.

Cheirmadurai K et al. in 2014 synthesized copper nanoparticles using henna leaf extract and their morphological characteristics were evaluated using transmission electron microscope. The TEM analysis revealed the crystalline spherical, shape of copper nanoparticles of size 25-30 nm synthesized from henna leaf. The UV-visible spectrum showed maximum absorption at 265 nm which confirmed the presence of active compound laws one [40]. The change of colour from blue to reddish brown indicated the formation of copper nanoparticles.

Similarly, Sampath M et al. in 2016 synthesized copper nanoparticles using *Eclipta prostrata* leaf extract and their morphological characteristics were evaluated using TEM [41]. TEM analysis revealed the crystalline face centric cubic shape of copper nanoparticles of size 23-50 nm. The UV-visible spectrum showed maximum absorption at 385 nm which confirmed the presence of copper nanoparticles.

Niharika N et al. in 2018 generated copper nanoparticles from *Azadirachta indica* leaves and their morphological characteristics were analyzed using UV-visible spectrophotometer. The biosynthesized copper nanoparticles were crystalline, spherical in shaped with the average size of 48nm. The highly stable copper

nanoparticles obtain the maximum absorption peak at 430 nm [42].

Amir K et al. in 2016 synthesized copper nanoparticles from coriander oleoresin extract and their morphological characteristics were analyzed using TEM [43]. The copper nanoparticles synthesized were crystalline spherical in shape of an average size of 20 nm. The UV-visible spectra showed a surface plasmon resonance at 560 nm.

The current study was conducted similar to the previous studies [16,18,19] and their characterization done using transmission electron microscope revealed similar results to the articles mentioned above. However further analysis must be done to study their antibacterial, anti inflammatory, antioxidant activities.

5. CONCLUSION

In this study, a simple, biological and low-cost approach was used for the preparation of copper Nanoparticles using blue Tea [44-57]. The green synthesized copper nanoparticles can be subjected to the various other biological activities such as antibacterial, antifungal, cytotoxic evaluation to know the efficiency of these nanoparticles do that they can be used as a substitute for conventional chemical products thereby reducing the cytotoxicity.

CONSENT

It is not applicable.

ETHICAL APPROVAL

It is not applicable.

COMPETING INTERESTS

Authors have declared that no competing interests exist.

REFERENCES

- Dhas NA, Arul Dhas N, Paul Raj C, Gedanken A. Synthesis, Characterization, and Properties of Metallic Copper Nanoparticles [Internet]. Chemistry of Materials. 1998;10:1446–52. Available:<http://dx.doi.org/10.1021/cm9708269>
- Dhas NA, Raj CP, Gedanken A. ChemInform Abstract: Synthesis, Characterization, and Properties of Metallic Copper Nanoparticles [Internet]. ChemInform. 2010;29. Available:<http://dx.doi.org/10.1002/chin.199832019>
- Nagar N, Devra V. Green synthesis and characterization of copper nanoparticles using Azadirachta indica leaves [Internet]. Materials Chemistry and Physics. 2018;213:44–51. Available:<http://dx.doi.org/10.1016/j.matchemphys.2018.04.007>
- Salavati-Niasari M, Davar F, Mir N. Synthesis and characterization of metallic copper nanoparticles via thermal decomposition [Internet]. Polyhedron. 2008;27:3514–8. Available:<http://dx.doi.org/10.1016/j.poly.2008.08.020>
- Rezazadeh L, Sharafi S, Schaffie M, Ranjbar M. Synthesis and characterization of magnetic nanoparticles from raffinate of industrial copper solvent extraction plants [Internet]. Materials Chemistry and Physics. 2019;229:372–9. Available:<http://dx.doi.org/10.1016/j.matchemphys.2019.03.023>
- Keihan AH, Veisi H, Veasi H. Green synthesis and characterization of spherical copper nanoparticles as organometallic antibacterial agent [Internet]. Applied Organometallic Chemistry. 2017;31:e3642. Available:<http://dx.doi.org/10.1002/aoc.3642>
- Biosynthesis and Characterization of Different Nanoparticles and Its Larvicidal Activity against Human Disease Vectors [Internet]. Marine Biomaterials. 2013;296–311. Available:<http://dx.doi.org/10.1201/b14723-18>
- Mohanpuria P, Rana NK, Yadav SK. Biosynthesis of nanoparticles: Technological concepts and future applications [Internet]. Journal of Nanoparticle Research. 2008;10:507–17. Available:<http://dx.doi.org/10.1007/s11051-007-9275-x>
- Rajakumar G, Rahuman AA. Phytosynthesis of Metal and Metal-Oxide Nanoparticles – Technological Concepts and Their Biomedical Applications [Internet]. Nanoparticles in the Fight Against Parasites. 2016;51–80. Available:http://dx.doi.org/10.1007/978-3-319-25292-6_5
- Mishra S, Dixit S, Soni S. Methods of Nanoparticle Biosynthesis for Medical and Commercial Applications [Internet]. Bio-Nanoparticles. 2015;141–54. Available:<http://dx.doi.org/10.1002/9781118677629.ch7>
- Khanna PK, Gaikwad S, Adhyapak PV, Singh N, Marimuthu R. Synthesis and characterization of copper nanoparticles [Internet]. Materials Letters. 2007;61:4711–4. Available:<http://dx.doi.org/10.1016/j.matlet.2007.03.014>
- J A, Aparna J, Rajeshkumar S. Cytotoxic and Antioxidant Activity of Zinc Oxide Nanoparticles Synthesised Using Maranta Arundinacea Root Extract [Internet]. International Journal of Research in Pharmaceutical Sciences. 2020;11:4372–7. Available:<http://dx.doi.org/10.26452/ijrps.v11i3.2655>
- Anti-Inflammatory Activity of Titanium Dioxide Nanoparticles Synthesised using Grape Seed Extract: An *in vitro* STUDY [Internet]. [Cited 2021 Aug 16]. Available:<https://paperpile.com/app/p/2fe87431-ef18-02f1-a4d4-c018f73e5b66>
- Efficacy of Aloe Vera Gel as an Adjunct to Scaling and Root Planing in the Management of Chronic Periodontitis [Internet]. [Cited 2021 Aug 16].

- Available:<https://paperpile.com/app/p/74fa086a-c658-0095-afbd-baccfb582a75>
15. Kishen A, Rajeshkumar S, Preejitha VB. Cynodon dactylon Mediated Synthesis of Selenium Nanoparticles and Its Antimicrobial Activity Against Oral Pathogens [Internet]. International Journal of Research in Pharmaceutical Sciences. 2020;11:4152–6. Available:<http://dx.doi.org/10.26452/ijrps.v11i3.2621>
 16. Rajeshkumar S, Nandhini NT, Manjunath K, Sivaperumal P, Krishna Prasad G, Alotaibi SS, et al. Environment friendly synthesis copper oxide nanoparticles and its antioxidant, antibacterial activities using Seaweed (*Sargassum longifolium*) extract [Internet]. Journal of Molecular Structure. 2021;1242:130724. Available:<http://dx.doi.org/10.1016/j.molstruc.2021.130724>
 17. Antifungal Activity of Grape Seed Extract Mediated Zinc Oxide Nanoparticles - An *In vitro* study [Internet]. [Cited 2021 Aug 16]. Available:<https://paperpile.com/app/p/d2434c40-e3a0-0fed-9ebe-2a13d846baf9>
 18. Synthesis and Characterization of Grape Seed Mediated Titanium Dioxide Nanoparticles: An *in vitro* study [Internet]. [Cited 2021 Aug 16]. Available:<https://paperpile.com/app/p/3479aa0f-9f72-0224-9cf3-85f5b6492e82>
 19. Green Synthesis of Selenium Nanoparticles (Senps) Using Aqueous Extract of Clove and Cinnamon [Internet]. [Cited 2021 Aug 16]. Available:<https://paperpile.com/app/p/8deb9cd6-c0cc-04e5-9d5b-a1a14726faac>
 20. Ramesh A, Varghese S, Jayakumar ND, Malaiappan S. Comparative estimation of sulfiredoxin levels between chronic periodontitis and healthy patients - A case-control study. J Periodontol [Internet]. 2018;89(10):1241–8. Available:<http://dx.doi.org/10.1002/JPER.17-0445>
 21. Paramasivam A, Priyadharsini JV, Raghunandhakumar S, Elumalai P. A novel COVID-19 and its effects on cardiovascular disease. Hypertens Res [Internet]. 2020;43(7):729–30. Available:<http://dx.doi.org/10.1038/s41440-020-0461-x>
 22. S G, T G, K V, Faleh A A, Sukumaran A, P N S. Development of 3D scaffolds using nanochitosan/silk-fibroin/hyaluronic acid biomaterials for tissue engineering applications. Int J Biol Macromol [Internet]. 2018;120(Pt A):876–85. Available:<http://dx.doi.org/10.1016/j.ijbiomac.2018.08.149>
 23. Del Fabbro M, Karanxha L, Panda S, Bucchi C, Nadathur Doraiswamy J, Sankari M, et al. Autologous platelet concentrates for treating periodontal infrabony defects. Cochrane Database Syst Rev [Internet]. 2018;26;11:CD011423. Available:<http://dx.doi.org/10.1002/14651858.CD011423.pub2>
 24. Paramasivam A, Vijayashree Priyadharsini J. MitomiRs: new emerging microRNAs in mitochondrial dysfunction and cardiovascular disease. Hypertens Res [Internet]. 2020;43(8):851–3. Available:<http://dx.doi.org/10.1038/s41440-020-0423-3>
 25. Jayaseelan VP, Arumugam P. Dissecting the theranostic potential of exosomes in autoimmune disorders. Cell Mol Immunol [Internet]. 2019;16(12):935–6. Available:<http://dx.doi.org/10.1038/s41423-019-0310-5>
 26. Vellappally S, Al Kheraif AA, Divakar DD, Basavarajappa S, Anil S, Fouad H. Tooth implant prosthesis using ultra low power and low cost crystalline carbon bio-tooth sensor with hybridized data acquisition algorithm [Internet]. Computer Communications. 2019;148:176–84. Available:<http://dx.doi.org/10.1016/j.comcom.2019.09.020>
 27. Vellappally S, Al Kheraif AA, Anil S, Assery MK, Kumar KA, Divakar DD. Analyzing Relationship between Patient and Doctor in Public Dental Health using Particle Memetic Multivariable Logistic Regression Analysis Approach (MLRA2). J Med Syst [Internet]. 2018;42(10):183. Available:<http://dx.doi.org/10.1007/s10916-018-1037-z>
 28. Varghese SS, Ramesh A, Veeraiyan DN. Blended Module-Based Teaching in Biostatistics and Research Methodology: A Retrospective Study with Postgraduate Dental Students. J Dent Educ [Internet]. 2019;83(4):445–50. Available:<http://dx.doi.org/10.21815/JDE.019.054>
 29. Venkatesan J, Singh SK, Anil S, Kim S-K, Shim MS. Preparation, Characterization and Biological Applications of Biosynthesized Silver Nanoparticles with Chitosan-

- Fucoidan Coating. *Molecules* [Internet]. 2018;23(6). Available: <http://dx.doi.org/10.3390/molecules23061429>
30. Alsubait SA, Al Ajlan R, Mitwalli H, Aburaisi N, Mahmood A, Muthurangan M, et al. Cytotoxicity of Different Concentrations of Three Root Canal Sealers on Human Mesenchymal Stem Cells. *Biomolecules* [Internet]. 2018;8(3). Available: <http://dx.doi.org/10.3390/biom8030068>
 31. Lee SY, Nielsen J, Stephanopoulos G. *Metabolic Engineering: Concepts and Applications* [Internet]. John Wiley & Sons. 2021;976. Available: <https://play.google.com/store/books/details?id=FoMxEAAAQBAJ>
 32. Vellappally S, Al Kheraif AA, Anil S, Wahba AA. IoT medical tooth mounted sensor for monitoring teeth and food level using bacterial optimization along with adaptive deep learning neural network [Internet]. Vol. 135, *Measurement*. 2019;672–7. Available: <http://dx.doi.org/10.1016/j.measurement.2018.11.078>
 33. PradeepKumar AR, Shemesh H, Nivedhitha MS, Hashir MMJ, Arockiam S, Uma Maheswari TN, et al. Diagnosis of Vertical Root Fractures by Cone-beam Computed Tomography in Root-filled Teeth with Confirmation by Direct Visualization: A Systematic Review and Meta-Analysis. *J Endod* [Internet]. 2021;47(8):1198–214. Available: <http://dx.doi.org/10.1016/j.joen.2021.04.022>
 34. R H, Hannah R, Ramani P, Tilakaratne WM, Sukumaran G, Ramasubramanian A, et al. Author response for “Critical appraisal of different triggering pathways for the pathobiology of pemphigus vulgaris—A review” [Internet]; 2021. Available: <http://dx.doi.org/10.1111/odi.13937/v2/response1>
 35. Ezhilarasan D, Lakshmi T, Subha M, Deepak Nallasamy V, Raghunandhakumar S. The ambiguous role of sirtuins in head and neck squamous cell carcinoma. *Oral Dis* [Internet]; 2021. Available: <http://dx.doi.org/10.1111/odi.13798>
 36. Sarode SC, Gondivkar S, Sarode GS, Gadball A, Yuwanati M. Hybrid oral potentially malignant disorder: A neglected fact in oral submucous fibrosis. *Oral Oncol* [Internet]. 2021;105390. Available: <http://dx.doi.org/10.1016/j.oraloncology.2021.105390>
 37. Kavarthapu A, Gurumoorthy K. Linking chronic periodontitis and oral cancer: A review. *Oral Oncol* [Internet]. 2021;105375. Available: <http://dx.doi.org/10.1016/j.oraloncology.2021.105375>
 38. Vellappally S, Al-Kheraif AA, Anil S, Basavarajappa S, Hassanein AS. Maintaining patient oral health by using a xeno-genetic spiking neural network [Internet]. *Journal of Ambient Intelligence and Humanized Computing*; 2018. Available: <http://dx.doi.org/10.1007/s12652-018-1166-8>
 39. Aldhuwayhi S, Mallineni SK, Sakhamuri S, Thakare AA, Mallineni S, Sajja R, et al. Covid-19 Knowledge and Perceptions Among Dental Specialists: A Cross-Sectional Online Questionnaire Survey. *Risk Manag Healthc Policy* [Internet]. 2021;14:2851–61. Available: <http://dx.doi.org/10.2147/RMHP.S306880>
 40. Dipankar C, Murugan S. The green synthesis, characterization and evaluation of the biological activities of silver nanoparticles synthesized from *Iresine herbstii* leaf aqueous extracts [Internet]. *Colloids and Surfaces B: Biointerfaces*. 2012;98:112–9. Available: <http://dx.doi.org/10.1016/j.colsurfb.2012.04.006>
 41. Sathishkumar G, Gobinath C, Wilson A, Sivaramakrishnan S. *Dendrophthoe falcata* (L.f) Ettingsh (Neem mistletoe): A potent bioresource to fabricate silver nanoparticles for anticancer effect against human breast cancer cells (MCF-7) [Internet]. *Spectrochimica Acta Part A: Molecular and Biomolecular Spectroscopy*. 2014;128:285–90. Available: <http://dx.doi.org/10.1016/j.saa.2014.02.096>
 42. Dang TMD, Le TTT, Fribourg-Blanc E, Dang MC. The influence of solvents and surfactants on the preparation of copper nanoparticles by a chemical reduction method [Internet]. *Advances in Natural Sciences: Nanoscience and Nanotechnology*. 2011;2:025004.

- Available:<http://dx.doi.org/10.1088/2043-6262/2/2/025004>
43. Singh OV. Bio-Nanoparticles: Biosynthesis and Sustainable Biotechnological Implications [Internet]. John Wiley & Sons. 2015;384.
Available:https://books.google.com/books/about/Bio_Nanoparticles.html?hl=&id=1AMSCAAAQBAJ
 44. Danda AK. Comparison of a single noncompression miniplate versus 2 noncompression miniplates in the treatment of mandibular angle fractures: A prospective, randomized clinical trial. *J Oral Maxillofac Surg* [Internet]. 2010;68(7):1565–7.
Available:<http://dx.doi.org/10.1016/j.joms.2010.01.011>
 45. Robert R, Justin Raj C, Krishnan S, Jerome Das S. Growth, theoretical and optical studies on potassium dihydrogen phosphate (KDP) single crystals by modified Sankaranarayanan–Ramasamy (mSR) method [Internet]. *Physica B: Condensed Matter*. 2010;405:20–4.
Available:<http://dx.doi.org/10.1016/j.physb.2009.08.015>
 46. Krishnan V, Lakshmi T. Bioglass: A novel biocompatible innovation. *J Adv Pharm Technol Res* [Internet]. 2013 Apr;4(2):78–83.
Available:<http://dx.doi.org/10.4103/2231-4040.111523>
 47. Soh CL, Narayanan V. Quality of life assessment in patients with dentofacial deformity undergoing orthognathic surgery—A systematic review [Internet]. *International Journal of Oral and Maxillofacial Surgery*. 2013;42:974–80.
Available:<http://dx.doi.org/10.1016/j.ijom.2013.03.023>
 48. Lekha L, Kanmani Raja K, Rajagopal G, Easwaramoorthy D. Schiff base complexes of rare earth metal ions: Synthesis, characterization and catalytic activity for the oxidation of aniline and substituted anilines [Internet]. *Journal of Organometallic Chemistry*. 2014;753:72–80.
Available:<http://dx.doi.org/10.1016/j.jorganchem.2013.12.014>
 49. Dhinesh B, Isaac Joshua Ramesh Lalvani J, Parthasarathy M, Annamalai K. An assessment on performance, emission and combustion characteristics of single cylinder diesel engine powered by *Cymbopogon flexuosus* biofuel [Internet]. *Energy Conversion and Management*. 2016;117:466–74.
Available:<http://dx.doi.org/10.1016/j.enconman.2016.03.049>
 50. Pradeep Kumar AR, Shemesh H, Jothilatha S, Vijayabharathi R, Jayalakshmi S, Kishen A. Diagnosis of Vertical Root Fractures in Restored Endodontically Treated Teeth: A Time-dependent Retrospective Cohort Study. *J Endod* [Internet]. 2016;42(8):1175–80.
Available:<http://dx.doi.org/10.1016/j.joen.2016.04.012>
 51. Vijayakumar GNS, Nixon Samuel Vijayakumar G, Devashankar S, Rathnakumari M, Sureshkumar P. Synthesis of electrospun ZnO/CuO nanocomposite fibers and their dielectric and non-linear optic studies [Internet]. *Journal of Alloys and Compounds*. 2010;507:225–9.
Available:<http://dx.doi.org/10.1016/j.jallcom.2010.07.161>
 52. Kavitha M, Subramanian R, Narayanan R, Udhayabanu V. Solution combustion synthesis and characterization of strontium substituted hydroxyapatite nanocrystals [Internet]. *Powder Technology*. 2014;253:129–37.
Available:<http://dx.doi.org/10.1016/j.powtec.2013.10.045>
 53. Sahu D, Kannan GM, Vijayaraghavan R. Size-Dependent Effect of Zinc Oxide on Toxicity and Inflammatory Potential of Human Monocytes [Internet]. *Journal of Toxicology and Environmental Health, Part A*. 2014;77:177–91.
Available:<http://dx.doi.org/10.1080/15287394.2013.853224>
 54. Neelakantan P, Cheng CQ, Mohanraj R, Sriraman P, Subbarao C, Sharma S. Antibiofilm activity of three irrigation protocols activated by ultrasonic, diode laser or Er:YAG laser *in vitro* [Internet]. *International Endodontic Journal*. 2015;48:602–10.
Available:<http://dx.doi.org/10.1111/iej.12354>
 55. Lekha L, Kanmani Raja K, Rajagopal G, Easwaramoorthy D. Synthesis, spectroscopic characterization and antibacterial studies of lanthanide(III) Schiff

- base complexes containing N, O donor atoms [Internet]. Journal of Molecular Structure. 2014;1056(1057):307–13. Available:<http://dx.doi.org/10.1016/j.molstruc.2013.10.014>
56. Gopalakannan S, Senthilvelan T, Ranganathan S. Modeling and Optimization of EDM Process Parameters on Machining of Al 7075-B4C MMC Using RSM [Internet]. Procedia Engineering. 2012;38:685–90. Available:<http://dx.doi.org/10.1016/j.proeng.2012.06.086>
57. Parthasarathy M, Isaac Joshua Ramesh Lalvani J, Dhinesh B, Annamalai K. Effect of hydrogen on ethanol-biodiesel blend on performance and emission characteristics of a direct injection diesel engine. Ecotoxicol Environ Saf [Internet]. 2016;134(Pt 2):433–9. Available:<http://dx.doi.org/10.1016/j.ecoenv.2015.11.005>

© 2021 George et al.; This is an Open Access article distributed under the terms of the Creative Commons Attribution License (<http://creativecommons.org/licenses/by/4.0>), which permits unrestricted use, distribution, and reproduction in any medium, provided the original work is properly cited.

Peer-review history:

The peer review history for this paper can be accessed here:
<https://www.sdiarticle5.com/review-history/77923>